

ENVITM
SURFACES



BRUTALIST

porcelain tile | *concrete collection* | vol.1

FIELD TILE

Matte or Polished | Rectified - 8mm



48"x48" (matte only)	24"x24"
Met	Met
Trellick	Trellick
Genex	Habitat
Geisel	Genex
	Tricorn
	Geisel



24"x48"	12"x24"
Met	Met
Trellick	Trellick
Habitat	Habitat
Genex	Genex
Tricorn	Tricorn
Geisel	Geisel

PAVERS

Matte | Rectified - 20mm



24"x24"
Met
Trellick
Genex



24"x48"	12"x48"
Met	Met
Trellick	Trellick
Genex	Genex

MOSAICS

Matte or Polished - 8mm



12"x12"

- Met
- Trellick
- Habitat
- Genex
- Tricorn
- Geisel

Met

Trellick

Habitat

Genex

Tricorn

Geisel




TRIMS



Cove Base

6"x12" x 7mm
special order only

Met
Trellick
Habitat
Genex
Tricorn
Geisel



Bullnose

3"x24"
Matte or Polished

Met
Trellick
Habitat
Genex
Tricorn
Geisel

TECHNICAL SPECIFICATIONS


	PHYSICAL PROPERTIES	TEST METHOD	REFERENCE VALUE	TEST RESULTS
	DCOF (Coefficient of Friction)	ANSI A326.3	≥ 0.42 wet*	≥ 0.42 wet
	Water Absorption	ASTM C373	Impervious ≤ 0.5%	≤ 0.4%
	Thickness Dimension	ASTM C499	Range ± 0.04 in.	≤ ± 0.04 in.
	Wedging (Rectified)	ASTM C502	± 0.25%	± 0.25%
	Wedging (Calibrated)	ASTM C502	± 0.50%	± 0.50%
	Warpage Edge (Rectified)	ASTM C485	± 0.40%	± 0.40%
	Warpage Diag. (Rectified)	ASTM C485	± 0.40%	± 0.40%
	Warpage Edge (Calibrated)	ASTM C485	± 0.50%	± 0.50%
	Warpage Diag. (Calibrated)	ASTM C485	± 0.50%	± 0.50%
	Breaking Strength (8mm)	ASTM C648	≥ 250 lbf	≥ 300 lbf
	Breaking Strength (2cm)	ASTM 1505	≥ 2,000 lbf	≥ 2,500 lbf
	Wear Resistance	ANSI A137.1	Wear properties of glazed porcelain	Suitable for residential/commercial
	Frost Resistance	ASTM C1026	No evident damage	No evident damage
	Chemical Resistance	ASTM C650	No evident damage	No evident damage
	Stain Resistance	ASTM C1378	No evident damage	No evident damage

All values are given for Matte or Honed material. No values are given for Polished material. We do not recommend polished surfaces in areas subject to exposure from grease, oil or water. The above information is subject to change. Individual product testing can be conducted by request. Tile is made with natural materials; therefore, it is subject to variation in color and/or veining.

V2 - Slight Variation



PRODUCT CERTIFIED FOR LOW CHEMICAL EMISSIONS: UL.COM/GG UL 2818



Met
Trellick
Habitat
Genex
Tricorn
Geisel